

CRYSTALLIZATION MACHINE FOR A MOUTH ON A PLASTIC BOTTLE BLANK

BACKGROUND OF THE INVENTION

1. Field of the Invention

5 The present invention relates to a crystallization machine for a mouth on a plastic bottle blank, and, particularly, to a crystallization machine, which can enhance the production efficiency and the quality while the plastic bottle blank is treated for crystallizing the mouth thereof.

10 2. Description of Related Art

Now, applying a single infrared radiation to perform the heating job in the crystallization machine for a mouth on a plastic bottle has been adopted conventionally in the whole world. The heat energy from the heat source of infrared radiation is sent to the outer surface of the mouth on a plastic bottle blank directly, and the mouth is crystallized during the process of heating. The crystallization conducted by the conventional crystallization machine gets involved in the following shortcomings:

20 (1) The mouth is easily deformed to change the configuration thereof resulting from absorbing the radiation unevenly due to the threaded area of the mouth being made with irregular screw threads and a non-homogeneous thickness.

25 (2) In order to avoid the phenomenon of being deformed during stripping, the mouth of the plastic bottle blank usually is cooled excessively, but the over cooled mouth makes the stripping job more difficult to perform.

30 (3) The temperature at the inner side of the mouth is not possible to be controlled properly so that it makes the above two problems worse.

(4) In order to keep a good shape and a precise dimension for the mouth and perform a smooth stripping job, it is not possible for the conventional crystallization machine to increase the speed of the production in a very limited processing window.

(5) The cycling conveyer mechanism for delivering the plastic bottle in the conventional crystallization machine usually is designed to move around horizontally such that it provides a very large size but a small capability so that the beneficial result of economics thereof is unfavorable.

Accordingly, the subject with regard to the deficiencies of the conventional crystallization machine is worth us to overcome although it may provide the basic function thereof and has its economic value.

SUMMARY OF THE INVENTION

The present invention adopts two sets of radiation heat sources in conjunction with an operation of an integrated machine system to increase the production in addition to the accurate size thereof being needed to maintain so as to solve the problems confronted by the conventional crystallization machine such as a difficultly operated production system and a low efficiency of production.

An object of the present invention is to provide a crystallization machine for a mouth on a plastic bottle blank, in which a shift device and a loader device are arranged to move synchronously such that the plastic bottle blank can fit with the loader device reliably and move correctly during being fed into the machine.

Another object of the present invention is to provide

054332-083101

a crystallization machine for a mouth on a plastic bottle blank, in which a stripping tool will not contact an opening end of the mouth on the plastic bottle blank and the threaded area thereof to keep an accurate dimension of the mouth without being deformed.

A further object of the present invention is to provide a crystallization machine for a mouth on a plastic bottle blank, in which a closed feed back system with a pyrometer are arranged therein to control the temperature at the inner side of the plastic bottle blank in a range of 70°C~200°C for maintaining an unchanged dimension of the bottle blank during stripping.

A further object of the present invention is to provide a crystallization machine for a mouth on a plastic bottle blank, in which a dual conveying system with a vertically moving cycle is adopted such that the crystallization machine can occupy a less space to treat multiple times of plastic bottle blanks with a least production cost.

A further object of the present invention is to provide a crystallization machine for a mouth on a plastic bottle blank, which can increase the production efficiency in addition to an accurate crystallized size being obtained.

A further object of the present invention is to provide a crystallization machine for a mouth on a plastic bottle blank, which can increase the effectiveness of a heater zone therein to decrease a waste of energy in the heater therein.

BRIEF DESCRIPTION OF THE DRAWINGS

The present invention can be more fully understood by reference to the following description and accompanying drawings, in which:

Fig. 1 is a diagrammatic view of a crystallization machine for a mouth on a plastic bottle blank according to the present invention illustrating a front half part thereof;

Fig. 2 is a diagrammatic view of a crystallization machine
5 for a mouth on a plastic bottle blank according to the present invention illustrating a rear half part thereof;

Fig. 3A is a diagrammatic view of input zone in the crystallization machine for a mouth on a plastic bottle blank;

Fig. 3B is a perspective view of a shift device in the
10 input zone of the crystallization machine for a mouth on a plastic bottle blank according to the present invention;

Fig. 3C is a diagrammatic view of a loader on a conveyer contacting with a transmission gear disk in the shift device according to the present invention;

Fig. 3D is a perspective view illustrating a plastic
15 bottle blank fitting with the loader in the shift device;

Fig. 4 is a plan view of locating wheels at the upper portion of the crystallization machine of the present invention;

Fig. 5 is a diagrammatic view of a heater zone at the
20 upper portion of the crystallization machine of the present invention;

Fig. 6 is an enlarged plan view of the heater zone shown in Fig. 5;

Fig. 7A is a diagrammatic view of a releasing zone in the
25 crystallization machine for a mouth on a plastic bottle blank according the present invention;

Fig. 7B is a side view of Fig. 7A;

Fig. 8 is a plan view of a stripping plate attached to
30 the loader device illustrating the stripping plate in a state

0904373P-083101
TOP SECRET

of performing to detaching the plastic bottle blank; and

Fig. 9 is a diagrammatic view illustrating two temperature sensors attached to the crystallization machine for a mouth on a plastic bottle blank of the present invention.

5

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Referring to Figs. 1, and 2, a crystallization machine 10 for a mouth on a plastic bottle blank according to the present invention provides a motor 11 to drive a front conveyer gear disk 12 and the conveyer gear disk 12 actuates a conveyer (not shown) to move above and below a heater zone 16. The crystallization machine 10 at the front end thereof is fixedly disposed a respective feed element 13 near both lateral sides thereof. The respective feed element 13 extends inward in a tilt way to connect with a shift device 14. The shift device 14 is fixedly located under the conveyer and a positioning slide rail 15 is mounted between the front gear disk 12 and the shift device 14. The shift device 14 keeps bottle blanks 23 in a state of being upright during the process of crystallizing. The crystallization machine 10 at the rear portion thereof is a cooling zone 17 and a blowing device (not shown) with a blowing pipe 18 is provided at the back of the cooling zone 17. The outlet of the blowing pipe 18 is under a rear conveyer gear disk 12' disposed at the cooling zone and opposite to the front conveyer gear disk 12. A releasing track 19 is disposed in front of the rear conveyer gear disk 12' next to the blowing pipe 18. An output track 21 is disposed under the releasing track 19 and the outlet of the blowing pipe 18 faces the output track 21, that is, the wind from the blowing device blows toward the output track 21 so as to

09643732-083101

5

10

25

30

fixedly attached a transmission gear 241 to mesh with the middle
 part of the loader 32 by way of a teeth part 242 thereof. As
 soon as the conveyer moves, the loader 32 can actuate the
 transmission gear 241 to rotate and cause the rotary disk 24
 5 to rotate via the central shaft 240. As it has been mentioned
 previously, the periphery of the rotary disk 24 has a gear
 like shape so that there are receiving recesses 243 provided
 for receiving the bottle blanks respectively. Hence, the bottle
 blanks 23 received in the respective recess 243 are inserted
 10 by the support post 322 of one of the loaders 32 respectively
 such that the bottle blanks 23 are moved by the loaders 32
 respectively as soon as the conveyer moves along with the
 loaders 32. In the mean time, the respective loader 32 carrying
 the respective bottle blank 23 can be sleeved into the
 15 respective bottle blank 23 while the bottle blanks 23 inter ^{enter?}
 the positioning rail 15 and ascend along the guide surface
 26. This is a design that each bottle blank 23 to be treated
 in the crystallizing machine 10 is corresponding to one of
 the loaders 32 on the conveyor and the conveyor and the shift
 20 mechanism 14 can be performed by a set of driving system instead
 of two sets of different driving systems. Therefore, the bottle
 blanks 23 can move with the loaders 32 synchronously to overcome
 the puzzle resulting from the need of adjusting the movement
 of the respective bottle blank 23 in accordance with the
 25 respective loader 32.

Referring to Fig. 3C, the loader 32 provides a fitting
 section 321 for fitting with the mouth of a bottle blank and
 a contact part 32 next to and above the fitting section 321
 for contacting with the transmission gear disk 241 instead
 30 of the fitting section 321 being contacted by the transmission

gear disk 241. In this way, it is possible for the fitting section 321 to avoid the outer diameter thereof being worn out and to fit with the inner diameter of the mouth on the bottle blank well afterward so that even if the transmission
5 gear disk 241 is made of metal instead of the engineering plastics, it is not necessary to worry about the problem of the fitting section being worn out.

Referring to Fig. 3D, a fixing base 247 is disposed between two rotary disks 24, which are corresponding to the
10 two parallel conveyers respectively and it is noted that one rotary disk is shown in Fig. 3 only, and the fixing base 247 at the upper end thereof is fixedly attached with two rollers 248 opposite to each other and corresponding to the two rotary disks 24 respectively. Each rotary disk 24 is slidably attached
15 with a plurality wedge blocks 244 and each wedge block 244 at the top thereof is urged by a spring 246 and the bottom thereof is a tilt plane 245. When the respective rotary disk 24 at both lateral sides of the fixing base 247 rotate, each wedge block 244 thereon rotates synchronously and the tilt
20 plane 245 touches the respective roller 248 so that the wedge block 244 can move upward at the same time to push the bottle blank 23 moving upward. In this way, the threaded part of the bottle blank 23 may higher than the guide rail 15 to allow the mouth of the bottle blank 23 piercing the support post
25 322 so that the bottle blank 23 can be moved outward to enter the positioning slide rail 15 with the support post 233. Thus, the bottle blank 23 can move along the positioning slide rail 15 such that the bottle blank 23 can move upward gradually to enter the heater zone for being heated up and the mouth
30 thereof can fit with the loader 32 completely at the same time.

Referring to Figs. 4, 5 and 6, a plurality of locating wheels 27 and a heater zone 16 are disposed at the upper portion of the crystallization machine 10 and the bottle blank 23 is delivered to the heater zone 16 by way of the actuation of the front conveyer gear disk 12. The bottle blank 23 passes over a passage between the locating wheels 27 and two opposite sides of the bottle blank 23 are pressed down by the locating wheels 27 to have the mouth of the bottle blank fitting with the loader 32 completely. The heater zone 16 at both lateral sides thereof provides an upper heat source 29 and a lower heat source 30 respectively and the upper heat source 29 at the upper end thereof has a cover shade 28 to prevent the heat source from expanding upward. The heat from the upper heat source 29 directs to the threaded part of the mouth on a bottle and the heat from the lower heat source 30 directs to the root of the loader 32 such that the heat can be transferred to inner surface of the threaded part in the bottle blank 23 and a proper temperature can be maintained in the respective plastic bottle blank 23 to facilitate the respective plastic bottle blank 23 being released easily. The support post 32 of the loader 32 presses against the inner side of the lower part of the bottle blank 23 to prevent the threaded part thereof from softening due to the heat during the process of crystallizing and from being deformed due to the weight of the respective plastic bottle blank 23 itself. The support post 322 has an air aperture 323 to discharge the air staying in the respective bottle blank 23 during heating and the discharged air can be removed to outside through the central part of the bottle blank. The respective loader 32 is fixedly attached to the conveying loaders 31, which connect with each other in series to form

2024年12月23日

Referring to Fig. 8, the stripping plate 33 provides a through hole 330 and an inner diameter of the through hole 330 is greater than the size of the threaded area on the mouth of the respective plastic bottle blank 23 so that the respective stripping plate 33 presses against the support ring 230 below to push the respective plastic bottle blank 23 away the

respective loader 32 to keep the end of the mouth 231 and the threaded area of the respective plastic bottle blank off being deformed and to maintain a precise dimension thereof. But, the conventional stripping job is performed by way of the
5 respective plastic bottle blank 23 being separated from the respective loader 32 from the mouth 231, and the mouth 231 may be deformed easily and becomes a defection.

Referring to Fig. 9, the temperature control sensor utilized in the present invention is composed of a closed loop
10 feed back control system with a non-contact type of pyrometer. But, it is noted that it is only for taking an example and other types of temperature control sensor may be used as long as it is suitable for the present invention.

The sensors 34, 35 are disposed at the rear side of
15 the heater zone 16, and the sensor 34 is used for sensing the temperature of the loader 32 and the sensor 35 is used for sensing the temperature at the threaded part of the bottle blank 23. The temperatures sensed by the sensors 34, 35 are fed back to the closed loop control system and control system
20 then controls and adjusts the temperatures at the threaded area of the bottle blank and the loader 32 respectively. In this way, the threaded area of the mouth on the bottle blank can maintain a correct size and is feasible for being stripped off the loader.

25 It is appreciated that the features of the present invention can be summarized hereinafter:

(1) The bottle blanks are delivered by way of double conveyers so that it is possible to speed up the treatment of crystallization for the bottle blanks and increase the
30 productivity.

(2) The stripping device does not affect the original size of the respective bottle blank, especially at the most important part thereof, while the bottle blank is complete for the treatment of crystallization and is released from the crystallization machine. Hence, the rate of defection resulting from the deformation can be lowered substantially.

(3) The loader used in the present invention can be controlled by a closed loop sensing system so that the temperature of the loader can be controlled steadily. Hence, the bottle blank can be stripped from the loader easily to maintain the crystallized product in a state of stable and high quality.

(4) Comparing to the conventional crystallization machine, a much higher efficiency for the production of the present invention can be obtained so that the economic effect resulting from the production of the present invention can be reached desirably.

Apparently, it can be made a general comment that the present invention not only enhances the crystallizing effect for the plastic bottle blank but also overcomes the defects with regard to the mouth of the bottle blank being deformed easily during being stripped and the difficulty resulting from stripping the plastic bottle blank. In the meantime, the capacity of production provided by the crystallization machine can be expanded easily as soon as the heater zone is extended in length thereof and the running speed of the crystallization machine is increased. Therefore, the quality of the crystallized mouth of the plastic bottle blank can be promoted substantially through the treatment of the present invention so that the present invention is a great breakthrough

in the field of crystallization machine for treating the mouth
of a plastic bottle blank.

While the invention has been described with reference
to the preferred embodiment, it is to be understood that
5 modifications or variations may be easily made without
departing from the spirit of the invention, which is defined
by the appended claims.

10

15

20

25

30

05943732-083101
TOP SECRET